

LNP™ LUBRICOMP™ COMPOUND ECL36XXQ

ECL36XXQ
REGION AMERICAS

DESCRIPTION

LNP* LUBRICOMP* ECL36XXQ is a compound based on Polyetherimide containing 30% Carbon Fiber, 15% PTFE. Added feature of this material is: Wear Resistant.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	222	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	0.9	%	ASTM D 638
Tensile Modulus, 5 mm/min	32860	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	324	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	26300	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	226	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1	%	ISO 527
Tensile Modulus, 1 mm/min	30420	MPa	ISO 527
IMPACT			
Izod Impact, unnotched, 23°C	413	J/m	ASTM D 4812
Izod Impact, notched, 23°C	69	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	11	J	ASTM D 3763
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	208	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.39	-	ASTM D 792
Density	1.39	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.01 – 0.05	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.1 – 0.4	%	ASTM D 955
Poisson's Ratio	0.43	-	ASTM E 132
Wear Factor Washer	22	10 ⁻⁴ -10 in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified: Manual

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dynamic COF	0.39	-	ASTM D 3702 Modified: Manual
Static COF	0.42	-	ASTM D 3702 Modified: Manual
ELECTRICAL			
Surface Resistivity	1.E+02 – 1.E+04	Ohm	ASTM D 257
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	360 – 365	°C	
Front - Zone 3 Temperature	365 – 375	°C	
Middle - Zone 2 Temperature	355 – 365	°C	
Rear - Zone 1 Temperature	345 – 355	°C	
Mold Temperature	120 – 150	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.