

VALOX™ FR RESIN ENH8530

REGION EUROPE

DESCRIPTION

Non-Brominated & Non-Chlorinated Flame Retardant, 15% Glass fiber reinforced PBT/PET blend

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	75	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	75	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 5 mm/min	7200	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	110	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	110	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	6000	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	75	MPa	ISO 527
Tensile Stress, break, 5 mm/min	75	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	7400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	125	MPa	ISO 178
Flexural Stress, break, 2 mm/min	125	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3	%	ISO 178
Flexural Modulus, 2 mm/min	6300	MPa	ISO 178
Hardness, H358/30	142	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	23	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	20	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	330	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	280	J/m	ASTM D 4812
Izod Impact, notched, 23°C	45	J/m	ASTM D 256
Izod Impact, notched, 0°C	45	J/m	ASTM D 256
Izod Impact, notched, -30°C	45	J/m	ASTM D 256

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched 80*10*4 +23°C	22	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	20	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	5	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	5	kJ/m ²	ISO 179/2C
THERMAL			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D 1525
Vicat Softening Temp, Rate B/50	202	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	190	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.1E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	4.6E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.65E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	215	°C	ISO 306
Vicat Softening Temp, Rate B/50	196	°C	ISO 306
Vicat Softening Temp, Rate B/120	200	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	215	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	180	°C	ISO 75/Af
Relative Temp Index, Elec	75	°C	UL 746B
Relative Temp Index, Mech w/impact	75	°C	UL 746B
Relative Temp Index, Mech w/o impact	75	°C	UL 746B
PHYSICAL			
Specific Gravity	1.46	-	ASTM D 792
Filler Content	15	%	ASTM D 229
Melt Flow Rate, 265°C/2.16kgf	20	g/10 min	ASTM D 1238
Melt Volume Rate, MVR at 250°C/5 kg	11	cm ³ /10 min	ASTM D 1238
Density	1.46	g/cm ³	ISO 1183
Melt Flow Rate, 250°C/5.0 kg	15	g/10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/1.2 kg	5	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/2.16 kg	13	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	45	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	145	Pa-s	ISO 11443
ELECTRICAL			
Volume Resistivity	1.E+15	Ohm-cm	ASTM D 257

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dielectric Strength, in oil, 0.8 mm	38	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	28	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	19	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	3.3	-	ASTM D 150
Dissipation Factor, 1 MHz	0.01	-	ASTM D 150
Hot Wire Ignition {PLC}	0	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
Volume Resistivity	1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	38	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	28	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	19	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.3	-	IEC 60250
Dissipation Factor, 1 MHz	0.01	-	IEC 60250
Comparative Tracking Index	400	V	IEC 60112
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating (3)(4)	1.5	mm	UL 94 by SABIC-IP
UL Recognized, 94V-0 Flame Class Rating (3)	1.5	mm	UL 94
UL Recognized, 94-5VA Rating (3)	2	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.0 mm	800	°C	IEC 60695-2-13
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 285	°C	
Nozzle Temperature	265 – 275	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	255 – 280	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	60 – 110	°C	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.