

## Noryl GTX\* Resin GTX909

Americas: COMMERCIAL

400F (205C) HDT. 3.3 Notched Izod. Excellent chemical resistance

### Property

TYPICAL PROPERTIES <sup>(1)</sup>			
	Value	Unit	Standard
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	66	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	59	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	9	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	50	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	99	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2370	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	176	J/m	ASTM D 256
Izod Impact, notched, -30°C	106	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	40	J	ASTM D 3763
Instrumented Impact Energy @ peak, -30	24	J	ASTM D 3763
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	245	°C	ASTM D 1525
HDT, 0.45 MPa, 6.4 mm, unannealed	204	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	125	°C	ASTM D 648
CTE, -20°C to 150°C, flow	9.54E-05	1/°C	ASTM E 831
CTE, -20°C to 150°C, xflow	8.1E-05	1/°C	ASTM E 831
<b>PHYSICAL</b>			
Specific Gravity	1.13	-	ASTM D 792
Water Absorption, 24 hours	0.54	%	ASTM D 570
Water Absorption, equilibrium, 23C	4.4	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	1.3 - 1.7	%	SABIC Method
<b>ELECTRICAL</b>			
Volume Resistivity	4.4E+16	Ohm-cm	ASTM D 257
Surface Resistivity	1.7E+16	Ohm	ASTM D 257
Dielectric Strength, in oil, 3.2 mm	25.5	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	3.27	-	ASTM D 150
Relative Permittivity, 1 MHz	2.76	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.039	-	ASTM D 150
Dissipation Factor, 1 MHz	0.019	-	ASTM D 150

Source GMD, last updated:01/05/2000

### Processing

- Do NOT mix NORYL GTX\* resin with other grades of NORYL\* resins.

Parameter	Value	Unit
Injection Molding		
Drying Temperature	95 - 105	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs

Maximum Moisture Content	0.07	%
Minimum Moisture Content	0.02	%
Melt Temperature	270 - 295	°C
Nozzle Temperature	270 - 295	°C
Front - Zone 3 Temperature	265 - 295	°C
Middle - Zone 2 Temperature	260 - 295	°C
Rear - Zone 1 Temperature	255 - 295	°C
Mold Temperature	65 - 95	°C
Back Pressure	0.3 - 1.4	MPa
Screw Speed	20 - 100	rpm
Shot to Cylinder Size	30 - 50	%
Vent Depth	0.013 - 0.038	mm

Source GMD, last updated:01/05/2000

- Polystyrene and acrylic regrind are effective purging Materials. Use temperature range appropriate for particular purging resin.
- Regrind must also be dried. Maximum 25% regrind.
- Dry at recommended temperatures and times for optimum performance. Overdrying can cause loss of physical properties and/or create appearance defects. Do not exceed recommended basic drying time and temperature above or:
  - 4-8 hrs at 95°C (200°F), 10 hrs max
  - 6-12 hrs at 80°C (175°F), 16 hrs max
  - 8-16 hrs at 65°C (150°F), 24 hrs max
- Avoid melt temperature in excess of 300°C (575°F) and residence times over 6-8 minutes (may affect properties and/or appearance).
- Nozzle temperature controls assist in elimination of drool premature freeze-off.
- Shot sizes in excess of 50% barrel capacity can lead to difficulties in providing a consistent, homogenous plastic melt.

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

**Disclaimer :** THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

\* Noryl GTX is a trademark of the SABIC Innovative Plastics Company

