

LNP* Lubricomp* Compound RFL33

Europe-Africa-Middle East:
COMMERCIAL

Also known as: RFL-4033
Product Reorder Name: RFL33

LNP* Lubricomp* RFL33 is a compound based on Nylon 66 resin containing Glass Fiber, PTFE.

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, break, 5 mm/min	126	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3.5	%	ISO 527
Tensile Modulus, 1 mm/min	5900	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	176	MPa	ISO 178
Flexural Modulus, 2 mm/min	4800	MPa	ISO 178
IMPACT	Value	Unit	Standard
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL	Value	Unit	Standard
CTE, 23°C to 60°C, flow	3.9E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	9.5E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	261	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	243	°C	ISO 75/Af
PHYSICAL	Value	Unit	Standard
Mold Shrinkage on Tensile Bar, flow (2)	0.3 - 0.5	%	SABIC Method
Density	1.35	g/cm ³	ISO 1183

Source GMD, last updated:01/03/2007

Processing

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

Disclaimer : All information, recommendation or advice given by SABIC Innovative Plastics, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC Innovative Plastics Company, its subsidiaries and affiliates, such use is in

the exclusive responsibility of the user. SABIC Innovative Plastics Company, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

* LNP is a trademark of the SABIC Innovative Plastics Company

* Lubricomp is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company. All rights reserved